

**A.B.C.C.**

*Paints*

**١ - الدهانات الإنشائية**

**1- Construction paints**

**الدهانات الزيتية Solvent Base**

**A.B.C.C.**

*Paints*

Enamel

زيتي

### زيتي لماع جولدن

- الوصف** : دهان زيتي شديد اللمعة مؤسس على راتنج الألكيد غني بثاني أكسيد التيتانيوم .
- الخواص والاستعمال** : يستخدم كطبقة نهائية في نظام التشطيبات الزيتية الداخلية والخارجية والديكور ، يتميز بتغطيته العالية ومقاومته الشديدة للاصفرار بالإضافة إلى قابليته للتنظيف والدعك .
- المواصفات الفنية**
- الكثافة** : ١,١٠ تقريباً .
- المواد الصلبة** : ٤٠ % من الحجم .
- معدل الانتشار** : ١٣ م<sup>٢</sup>/لتر عند سماكة ٣٠ ميكرون يعتمد ذلك على طريقة الطلاء والسطح المراد طلائه .
- زمن الجفاف** : ٣-٤ ساعات يعتمد ذلك على درجة الحرارة وسماكة الدهان .
- زمن إعادة الطلاء** : ١٢ ساعة كحد أدنى عند درجة حرارة ٣٠ درجة مئوية .
- المظهر** : شديد اللمعة - أبيض .
- درجة الاشتعال** : ٣٩ درجة مئوية .
- طريقة الطلاء** : الفرشاة - الرولة - مسدس الرش .
- المخفف** : ABC TN01 .
- نسبة التخفيف** : يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
- إعداد السطح** : يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .

## Golden Gloss Enamel

### PRODUCT DESCRIPTION

A high quality alkyd gloss finish coat based on alkyd resin pigmented with titanium di-oxide and some other additives . It is specially designed to provide excellent hiding and gloss. This quality has been approved by SASO.

### PRODUCT USE

For interior and exterior use.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Gloss
Density gm/cc	1.10 +/- 0.02
Volume Solids %	40 %
Theoretical Coverage	13 sq. mt/ lt at 30 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 3-4 hours
Drying Time (H/D)	6-8 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	Satisfactory
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 12 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Golden Gloss Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use Undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the glossy finishes.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventillation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	0-10%
Recommended Thinner	ABC Thinner

d) Cleaning Solvent	ABC Thinner
---------------------	-------------

### زيتي لماع كلاسيك

- الوصف** : دهان زيتي مؤسس على راتنج الألكيد غني بثاني أكسيد التيتانيوم وبعض الملونات الأخرى .
- الخواص والاستعمال** : يستخدم كطبقة نهائية في نظام التشطيبات الزيتية الداخلية والخارجية والديكور ، يتميز بتغطيته العالية وقابليته للتنظيف والدعك
- المواصفات الفنية**
- الكثافة** : ٠,٩٨ تقريباً .
- المواد الصلبة** : ٣٧ % من الحجم .
- معدل الانتشار** : ١٢ م<sup>٢</sup>/لتر عند سماكة ٣٠ ميكرون .
- زمن الجفاف** : ٣-٤ ساعات يعتمد ذلك على درجة الحرارة وسماكة الدهان .
- زمن إعادة الطلاء** : ١٢ ساعة كحد أدنى .
- المظهر** : أبيض - لماع .
- درجة الاشتعال** : ٣٩ درجة مئوية .
- طريقة الطلاء** : الفرشاة - الرولة - مسدس الرش .
- المخفف** : ABC TN01 .
- نسبة التخفيف** : يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
- إعداد السطح** : يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .

## Classic Gloss Enamel

### PRODUCT DESCRIPTION

A good quality alkyd gloss finish coat based on alkyd resin pigmented with titanium di-oxide and some other additives . It is specially designed to provide good hiding and excellent gloss.

### PRODUCT USE

For interior and exterior use.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Gloss
Density gm/cc	0.98 +/- 0.02
Volume Solids %	37 %
Theoretical Coverage	12 sq. mt/ lt at 30 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 3-4 hours
Drying Time (H/D)	6-8 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	Satisfactory
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 12 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Classic Gloss Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use Undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the glossy finishes.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventilation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	0-10%
Recommended Thinner	ABC Thinner

#### d) Cleaning Solvent

	ABC Thinner
--	-------------



### زيتي لماع إقتصادي

- الوصف** : دهان زيتي لماع مؤسس على راتنج الألكيد غني بثاني أكسيد التيتانيوم .
- الخواص والاستعمال** : يستخدم كطبقة نهائية في نظام التشطيبات الزيتية الداخلية والخارجية والديكور ، سهل الدهن وسريع الجفاف ، قابل للتنظيف والدعك .
- المواصفات الفنية**
- الكثافة** : ١,٠٢ تقريباً .
- المواد الصلبة** : ٣٨ % من الحجم .
- معدل الانتشار** : ١٢,٥ م<sup>٢</sup>/ لتر عند سماكة ٣٠ ميكرون يعتمد ذلك على طريقة الطلاء والسطح المراد طلاؤه .
- زمن الجفاف** : ٣-٤ ساعات يعتمد ذلك على درجة الحرارة وسماكة الدهان .
- زمن إعادة الطلاء** : ١٢ ساعة كحد أدنى .
- المظهر** : لماع - أبيض .
- درجة الاشتعال** : ٣٩ درجة مئوية .
- طريقة الطلاء** : الفرشاة - الروله - مسدس الرش .
- المخفف** : ABC TN01 .
- نسبة التخفيف** : يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
- إعداد السطح** : - يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .  
- يجب طلاؤه عند درجات الحرارة العادية (١٠-٣٥) درجة مئوية
- إعدادات السلامة** : - يجب أن يكون المكان مزود بالتهوية المناسبة .  
- يجب حفظ المادة في مكان بارد وجاف .  
- عند الإصابة في العين يجب استعمال الماء ومن ثم استشارة الطبيب .

## Economy Gloss Enamel

### PRODUCT DESCRIPTION

A commercial quality alkyd gloss finish coat based on alkyd resin pigmented with titanium di-oxide and some other additives . It is specially designed to provide good hiding and gloss.

### PRODUCT USE

For interior and exterior use.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Semi-Gloss to gloss
Density gm/cc	1.02 +/- 0.02
Volume Solids %	38 %
Theoretical Coverage	12.5 sq. mt/ lt at 30 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 3-4 hours
Drying Time (H/D)	6-8 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	Satisfactory
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 12 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Economy Gloss Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use Undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the glossy finishes.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventilation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	0-10%
Recommended Thinner	ABC Thinner

d) Cleaning Solvent	ABC Thinner
---------------------	-------------

### زيتي نصف لماع جولدن

وصف	: دهان زيتي نصف لمعة عالي الجودة مؤسس على راتنج الألكيد يستعمل كطبقة نهائية في نظام الطلاء الزيتي .
الخواص والاستعمال	: يستعمل من الداخل والخارج لديه القدرة العالية على الاحتفاظ باللون ، سهل التنظيف والدعك ، قليل الاصفرار .
<u>المواصفات الفنية</u>	
الكثافة	: ١,٣٦ تقريباً .
المواد الصلبة	: ٥٦ % من الحجم .
معدل الانتشار	: ١٧-١٨ م <sup>٢</sup> /لتر عند سماكة ٣٠ ميكرون يعتمد ذلك على السطح المراد طلاؤه وطريقة الطلاء .
زمن الجفاف	: ٢-٤ ساعات يعتمد ذلك على درجة الحرارة .
زمن إعادة الطلاء	: ١٢ ساعة كحد أدنى عند درجة حرارة ٣٠ درجة مئوية .
المظهر	: أبيض - نصف لماع .
درجة الاشتعال	: ٣٨ درجة مئوية .
طريقة الطلاء	: الفرشاة - الرولة - مسدس الرش .
المخفف	: ABC TN01 .
نسبة التخفيف	: يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
إعداد السطح	: يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .

## Golden Semi Gloss Enamel

### PRODUCT DESCRIPTION

A premium quality alkyd semi-gloss finish coat based on alkyd resin pigmented with titanium di-oxide and some other inert pigments. It is specially designed to provide excellent hiding and flow.

### PRODUCT USE

For interior and exterior use.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Semi-gloss
Density gm/cc	1.36 +/- 0.02
Volume Solids %	56 %
Theoretical Coverage	17 - 18 sq. mt/ lt at 30 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 2 - 4 hours
Drying Time (H/D)	6 - 8 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	NA
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 12 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Golden Semi Gloss Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations. Use an undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the semi-gloss finishes.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application. Ensure proper ventilation during application and drying. Use mask during application. Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	5 - 10%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	10 - 15%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	5 - 10%
Recommended Thinner	ABC Thinner

#### d) Cleaning Solvent

	ABC Thinner
--	-------------

### زيتي نصف لماع كلاسيك

- الوصف** : دهان زيتي نصف لمعة عالي الجودة مؤسس على راتنج الألكيد يستعمل كطبقة نهائية في نظام الطلاء الزيتي .
- الخواص والاستعمال** : يستعمل من الداخل والخارج لديه القدرة العالية على الاحتفاظ باللون ، سهل التنظيف والدك ، قليل الاصفرار .
- المواصفات الفنية**
- الكثافة** : ١,١٣ تقريباً .
- المواد الصلبة** : ٣٧% من الحجم .
- معدل الانتشار** : ١٢ م<sup>٢</sup>/ لتر عند سماكة ٣٠ ميكرون يعتمد ذلك على السطح المراد طلائه وطريقة الطلاء .
- زمن الجفاف** : ٢ - ٤ ساعات يعتمد ذلك على درجة الحرارة .
- زمن إعادة الطلاء** : ١٢ ساعة كحد أدنى عند درجة حرارة ٣٠ درجة مئوية .
- المظهر** : أبيض - نصف لماع .
- درجة الاشتعال** : ٣٨ درجة مئوية .
- طريقة الطلاء** : الفرشاة - الروله - مسدس الرش .
- المخفف** : ABC TN01 .
- نسبة التخفيف** : يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
- إعداد السطح** : يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .

## Classic Semi Gloss Enamel

### PRODUCT DESCRIPTION

A superior quality alkyd semi-gloss finish coat based on alkyd resin pigmented with titanium di-oxide and some other inert pigments. It is specially designed to provide excellent hiding and flow.

### PRODUCT USE

For interior and exterior use.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Semi-gloss
Density gm/cc	1.13 +/- 0.02
Volume Solids %	37 %
Theoretical Coverage	12 sq. mt/ lt at 30 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 2-4 hours
Drying Time (H/D)	6-8 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	NA
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 12 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.



## Classic Semi Gloss Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use an undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the semi-gloss finishes.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventilation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### d) Cleaning Solvent

ABC Thinner

### زيتي نصف لماع إقتصادي

- الوصف** : دهان زيتي نصف لماع مؤسس على راتنج الالكيد ومطعم بثاني أكسيد التيتانيوم .
- الخواص والاستعمال** :  
● يستخدم للداخل والخارج .  
● مقاوم للإحتكاك  
● مقاوم جيد للغسيل ومواد التنظيف .  
● سهل الاستخدام .  
● الاحتفاظ بالألوان .
- المواصفات الفنية**
- الكثافة** : 1,11 ± 0,02
- المواد الصلبة** : 34% من الوزن .
- معدل الانتشار** : 11 / 2م للتر عند سماكة 30 ميكرون ويعتمد ذلك على السطح والأداة المستخدمة .
- زمن الجفاف** : 2 - 4 ساعات جفاف سطحي - 6 - 8 ساعات جفاف كلي .
- المظهر** : ناعم - و نصف لماع .
- درجة الاشتعال** : 38 درجة مئوية .
- طريقة الطلاء** : الرولة - الفرشاة - مسدس الرش الهوائي واللاهوائي .
- المخفف** : تتر بارد .
- نسبة التخفيف** : 10 - 15 %
- إعداد السطح** : يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت أو شحوم .

## Economy Semi Gloss Enamel

### PRODUCT DESCRIPTION

A good quality alkyd semi-gloss finish coat based on alkyd resin pigmented with titanium di-oxide and some other inert pigments. It is specially designed to provide good hiding and flow.

### PRODUCT USE

For interior and exterior use.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Semi-gloss
Density gm/cc	1.11 +/- 0.02
Volume Solids %	34 %
Theoretical Coverage	11 sq. mt/ lt at 30 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 2-4 hours
Drying Time (H/D)	6-8 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	NA
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 12 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Economy Semi Gloss Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use an undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the semi-gloss finishes.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventilation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### d) Cleaning Solvent

	ABC Thinner
--	-------------

### زيتي مطفي جولدن

- الوصف** : دهان زيتي مطفي مؤسس على راتنج الألكيد غني بثاني أكسيد التيتانيوم وكربونات الكالسيوم .
- الخواص والاستعمال** : يستعمل كطبقة نهائية في نظام التشطيبات الزيتية الداخلية ، لديه القدرة على الإخفاء ومقاومة الاصفرار والاحتفاظ باللون .
- المواصفات الفنية**
- الكثافة** : ١,٤٥ تقريباً .
- المواد الصلبة** : ٤٧ % من الحجم .
- معدل الانتشار** : ١٢ م<sup>٢</sup>/لتر عند سماكة ٣٥ ميكرون يعتمد ذلك على طريقة الطلاء والسطح المراد طلاؤه .
- زمن الجفاف** : ٢ ساعة يعتمد على ذلك على درجة الحرارة وسماكة الدهان .
- زمن إعادة الطلاء** : ١٢ ساعة كحد أدنى يعتمد ذلك على درجة الحرارة وسماكة الدهان .
- المظهر** : مطفي - أبيض .
- درجة الاشتعال** : ٣٨ درجة مئوية .
- طريقة الطلاء** : الفرشاة - الرولة - مسدس الرش .
- المخفف** : ABC TN01 .
- نسبة التخفيف** : يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
- إعداد السطح** : يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .

## Golden Flat Enamel

### PRODUCT DESCRIPTION

A superior quality alkyd flat finish coat based on alkyd resin pigmented with titanium di-oxide and some other inert pigments. It is specially designed to provide excellent hiding as approved by SASO.

### PRODUCT USE

For interior use only.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Matt
Density gm/cc	1.45 +/- 0.02
Volume Solids %	47 %
Theoretical Coverage	12 sq. mt/ lt at 35 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 2 hours
Drying Time (H/D)	4-6 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	NA
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 8 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Golden Flat Enamel

### PAINT SYSTEM ADVICES

#### a) For New Sustrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use undercoat as a build and adhesion coat.

#### b) Old Sustrates

Can be applied provided the surface is made suitable for the flat coat application.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventilation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	15-20%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### d) Cleaning Solvent

	ABC Thinner
--	-------------

### زيتي مطفي كلاسيك

- الوصف** : دهان زيتي مطفي مؤسس على راتنج الألكيد .
- الخواص والاستعمال** : يستخدم كطبقة نهائية في نظام التشطيبات الزيتية الداخلية والديكور، سريع الجفاف، ناعم اللمس .
- المواصفات الفنية**
- الكثافة** : ١,٤٦ تقريباً .
- المواد الصلبة** : ٤٦ % من الحجم .
- معدل الانتشار** : ١٢ - ١٣ م<sup>٢</sup>/لتر عند سماكة ٣٥ ميكرون يعتمد ذلك على طريقة الطلاء والسطح المراد طلاؤه .
- زمن الجفاف** : ٢ ساعة يعتمد ذلك على درجة الحرارة وسماكة الدهان .
- زمن إعادة الطلاء** : ٨ ساعة كحد أدنى عند درجة حرارة ٣٠ درجة مئوية .
- المظهر** : مطفي - أبيض .
- درجة الاشتعال** : ٣٨ درجة مئوية .
- طريقة الطلاء** : الفرشاة - الرولة - مسدس الرش .
- المخفف** : ABC TN01 .
- نسبة التخفيف** : يمكن التخفيف حتى ٢٠% يعتمد ذلك على طريقة الطلاء والأداة المستخدمة في الطلاء .
- إعداد السطح** : يجب أن يكون السطح نظيفاً ، جافاً خالياً من أي شوائب أو أغبرة أو زيوت .



## Classic Flat Enamel

### PRODUCT DESCRIPTION

A good quality alkyd flat finish coat based on alkyd resin pigmented with titanium di-oxide and some other inert pigments.

### PRODUCT USE

For interior use only.  
Good color retention properties.  
Good hiding and covering capacity.  
Good flow and drying properties  
Very good adhesion properties.  
Washable with good scrub resistance.  
Easy to apply.

### SUBSTRATES

Concrete, masonry, cement rendering and plasters, metals , woods etc.

### CHARACTERSTICS

Color	White or any requested color
Finish	Smooth
Gloss	Matt
Density gm/cc	1.46 +/- 0.02
Volume Solids %	46%
Theoretical Coverage	12-13 sq. mt/ lt at 35 micron DFT(depends upon the substrate condition & method of application)
Mixing Ratio	NA
Drying Time (S/D)	Approx 2 hours
Drying Time (H/D)	4-6 hours.( max)
Washability	NA
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	NA
Flash Point	38 deg. cel
Pot Life	NA
Overcoat Interval	Approx. 8 hours.
Shelf Life	12 months from date of production.

### SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.

## Classic Flat Enamel

### PAINT SYSTEM ADVICES

#### a) For New Substrates

Make sure that the surface is dry, clean and free from any other contaminations.  
Use undercoat as a build and adhesion coat.

#### b) Old Substrates

Can be applied provided the surface is made suitable for the flat coat application.

### APPLICATION DETAILS

Paint should be mixed thoroughly before the application.  
Ensure proper ventilation during application and drying.  
Use mask during application.  
Close the drum properly and clean the equipments once the application is over.

### APPLICATION GUIDELINE & INSTRUMENT FOR USE:

#### a) Brush, Roller & Others

Volume of Thinner	10-15%
Recommended Thinner	ABC Thinner

#### b) Air Spray

Volume of Thinner	15-20%
Recommended Thinner	ABC Thinner

#### c) Airless Spray

Volume of Thinner	5-10%
Recommended Thinner	ABC Thinner

#### d) Cleaning Solvent

ABC Thinner